technical datasheet

F3 PC-CF150

Dezember 2024

www.fiberthree.com

General information

Properties

- *Polycarbonate (modified)*
- *15% by weight carbon fibers*
- *good impact resistance*
- *low water absorption*
- *low warpage*
- *excellent adhesion to print bed*
- *exellent thermal stability up to 130°C*
- *very high stiffness*
- *matt surface (black)*


Mechanical properties	Test method	Unit	Typical value	Quality grade acc. VDI 3405 Part 7
Density	DIN EN ISO 1183	g/ cm³	1,25	
Modulus of Elasticity printed specimen x-y (0°) *	DIN EN ISO 527-2 Typ 1A *	MPa (N/mm²)	7.545	9
Modulus of Elasticity printed specimen x-y (90°) *	DIN EN ISO 527-2 Typ 1A *	MPa (N/mm²)	--	--
Tensile strength printed specimen x-y (0°) *	DIN EN ISO 527-2 Typ 1A *	MPa (N/mm²)	69	7
Tensile strength printed specimen x-y (+ 45°/-45°) *	DIN EN ISO 527-2 Typ 1A *	MPa (N/mm²)	--	--
Tensile strength printed specimen x-y (90°) *	DIN EN ISO 527-2 Typ 1A *	MPa (N/mm²)	--	--
Tensile stress printed specimen x-y (0°)	DIN EN ISO 527-2 Typ 1A*	MPa (N/mm²)	3	--
Elongation printed specimen (0°)	DIN EN ISO 527-2 Typ 1A*	%	--	--
Flexural modulus E_f printed specimen (+ 45°/-45°)	DIN EN ISO 14125 (Method B)	GPa (kN/mm²)	--	
Impact strength printed specimen	DIN EN ISO 179eU	kJ/m²	--	
Impact strength printed specimen (notched)	DIN EN ISO 179eB	kJ/m²	--	

* Test specimen printed: 1.75mm filament; v=50 mm/s; Orientation layers in 0°/ 90°/ +-45°; conditioned 24h at 50% RF and 23° C
Test specimen polycarbonate: Intamsys F410, nozzle 0.6mm, temp. nozzle 325°C, temp print bed 145°C; temp. build space 90°C, layer height 0.15mm


Tensile test PC with 1mm/min. These are target values for optimal print quality. Values might vary greatly with the same settings, depending on the system Nozzle - Printer - Gcode.

Orientation of printed specimen


X-Y-orientation (45°)



X-Y-orientation (90°)



X-Y-orientation (0°)



Thermal properties	Test method	Unit	Typical value
Glass transition temp.	DIN ISO 11357	°C	145
Heat distortion temp. (HDT A@1,8 MPa)	DIN ISO 75	°C	130
Electrical properties	**Test method**	**Unit**	**Typical value**
Insulation resistance	IEC 60167	Ohm*m	$>10^9$
Surface resistance	IEC 60093	Ohm*m	$>10^9$
Other properties	**Test method**	**Unit**	**Typical value**
Water absorption (after 24h)	DIN ISO 62	%	0,3
Recommendations	**Test method**	**Unit**	**Typical value**
Temperature nozzle	Fiberthree GmbH	°C	310 - 330
Temperature build plate	Fiberthree GmbH	°C	> 140
Temperature build chamber	Fiberthree GmbH	°C	> 80
Nozzle diameter	Fiberthree GmbH	mm	≥ 0,4
Material build plate	Fiberthree GmbH		carbon fiber, glass fiber or phenolic resins, glass
Recommended nozzle	Fiberthree GmbH		wear resistant nozzles: hardened steel, tungsten, nozzles with industrial sapphire or ruby or ceramic
Recommended parts	Fiberthree GmbH		Parts wit high elasticity & impact resistance as well as media resistance to UV radiation and acids

EU & REACH conformity

SVHC > 0,1 % (List dated December 2023)	given	no substances included
Regulated substances acc. 2015/863/EU (RoHS 3)	given	no substances included

Legal disclaimer

Technical properties or values are related to the thermoplastic base material for filament production if not mentioned differently.
Any recommendation made for use of seller's materials are made to the best knowledge and are based upon prior tests and experience of the seller. Seller does not guarantee the results to be obtained and all such recommendations are non-binding and do not constitute any representation and do not affect in any way buyer's obligation to examine and test the seller's goods with regard to their suitability for buyer's foreseen purposes.
No information given by the seller is to be construed in any way as a guarantee regarding charactaristics or duration of use, unless such information has been explicitly given as a guarantee.